



Process for preparing a polyol fine wax.

Patent Number: EP0416566
Publication date: 1991-03-13
Inventor(s): ANTBERG MARTIN DR (DE); ROHRMANN JUERGEN DR (DE); SPALECK WALTER (DE); WINTER ANDREAS DR (DE); DOLLE VOLKER DR (DE)
Applicant(s):: HOECHST AG (DE)
Requested Patent: ☒ EP0416566, A3, B1
Application Number: EP19900117039 19900905
Priority Number (s): DE19893929693 19890907
IPC Classification: C08F4/602 ; C08F10/00
EC Classification: C08F110/06, C08F110/06
Equivalents: AU6219090, AU625142, CA2024718, ☐ DE3929693, ES2135375T, JP3041024B2, ☐ JP3100004, ZA9007099

Abstract

If olefins of the formula  (R<9> and R<10> are H or C1-C28-alkyl) are polymerised using a catalyst comprising an aluminoxane and a metallocene of the formula I  in particular R<5>R<6>C(Ind)2ZrCl2 and R<5>R<6>C(Ind)2Zr(CH3)2, the isotacticity, and thus the hardness and melting point, of the polymer wax can be varied by simply changing the polymerisation temperature without at the same time significantly affecting the molecular weight of the polymer.

Data supplied from the esp@cenet database - I2